SUNNYSIDE BOILED LINSEED OIL

TECHNICAL DATA SHEET





# **BOILED LINSEED OIL**

## DESCRIPTION

Boiled Linseed Oil is extracted from the seed of the flax plant, with special additives to shorten its drying time. It is an extender and fortifier of oil based paints, stains and primers, and is a quality finish for fine woods, furniture and antiques.

## ITEM NUMERS & SIZES

 Pint
 Quart
 1-Gallon
 2.5-Gal.
 5-Gal.
 55-Gal.

 87216
 87232
 872G1
 872G5
 872G5

#### HAZARDOUS INGREDIENTS

Ingredient CAS# Percent

No Hazardous Ingredients by OSHA Definition.

# SAFETY INFORMATION

 HEALTH:
 1

 FIRE:
 1

 REACTIVITY:
 0

#### PRODUCT APPLICATION

Boiled Linseed Oil should be applied to unfinished wood only. Linseed oil must penetrate to be effective. Thin up to 2:1 with mineral spirits to ensure proper penetration. Boiled Linseed Oil can be added directly to oil based paints and stains, always follow the coatings manufacturer's directions.

# PHYSICAL PROPERTIES

V.O.C. (g/L)

Typical Properties	Results
GRAVITY, (60 °F)	
API	
SPECIFIC	0.94
DENSITY (Lb./GAL)	7.83
DISTILLATION RANGEE,° F.	≥300-IBP
FREEZING POINT, °F (°C)	
KAURI BUTANOL (Kb) VALUE	
ANILINE POINT, °F	
FLASH POINT, T.C.C. °F	≥200
FLAMMABLE LIMITS IN AIR, % BY VOLUME	
LOWER, AT 100°F (38°C)	
UPPER, AT 200°F (93°C)	
AUTOIGNITION TEMPERATURE, °F (°C)	
COLOR, SAYBOLT	
DOCTOR TEST	
CORROSION, 3 HRS. @ 212 °F	
NON-VOLATILES, g/100ml	
ACIDITY	
ALKALINITY (AS NH3, WT%)	
EVAPORATION RATE	Slower than ether
APPEARANCE	Clear, Amber color
ODOR	Mild Odor
VAPOR PRESSURE, mm Hg @ 20 °C	
REFRACTIVE INDEX, @ 20 °C	
SULFUR CONTENT, PPM	
PURITY, by G.C., Wt%	
WATER CONTENT, Wt%	
WATER MISCIBILITY	Negligible
DOT SHIPPING NAME	Not Regulated by US DOT as a Hazar
DOT CLASSIFICATION	
SHIPPING Wt. at 20 °C	7.83

These properties are repesentative of typical inspections. They do not constitute product specifications. Consult MSDS sheet for additional information.

0-Non Volatile

# **TEST METHOD** <u>ASTM</u> **Applied** D-278 D-1298 D-86 D-1133 D-611 D-56 D-1255 D-156 D-484 D-130 D-1353 D-847 D-1614 D-1296 D-1218 D-1266 D-1364 D-1722 dous Material

See MSDS sheeet for additional Health, Safety, Handling and Regulatory Information available on our website at www.sunnysidecorp.com/msds.html